

# AANBRENGCONDITIES DIGITEX 40° TRANSFERS

Materiaal	Temperatuur	Voorpersen	Min. Druk	Perstijd	Drager verwijderen	Napersen
100% katoen	160°-170° C	-	3 Kg/cm2	10 sec.	koud	Ja, 5 sec.
Katoen / polyester	160°-170° C	-	3 Kg/cm2	10 sec.	koud	Ja, 5 sec.
Beaver nylon, ongecoat	170°-180° C	-	3 Kg/cm2	10 sec.	koud	Ja, 5 sec.
Nylon, ongecoat	160° C	5 sec. ivm krimp	3 Kg/cm2	8 sec.	koud	Ja, 5 sec.
Polyester, ongecoat	160° C	5 sec. ivm krimp	3 Kg/cm2	8 sec.	koud	Ja, 5 sec.
Flexothane	140° C	---	3 Kg/cm2	5 sec.	koud	Ja, 5 sec.

*Bovengenoemde instellingen zijn slechts richtlijnen; e.e.a. is afhankelijk van het materiaal*



**kijk ook op:**  
[www.osch.nl](http://www.osch.nl)  
[www.digitextransfers.com](http://www.digitextransfers.com)

